

Technical Bulletin

Mixing Instructions For SuperStone™ System

(Note: 150 Pounds Of Aggregate 1 Portion Pack)

1. 1 Portion Pack consists of 2 containers. 1 container is marked Resin Part "A", the other container is marked Hardener Part "B". Pour contents of hardener into Resin.

2. SHAKE CONTENTS FOR 3 TO AS MUCH AS 10 MINUTES, depending upon temperature. (The higher the temperature, the lower the mixing time to minimum of 3 minutes).

3. Start mixer (with aggregate in) and pour combined SuperStone mix into mixer. Mix for 6 minutes. NOTE: If mixing in mortar box, 6 minutes will be sufficient if aggregate is agitated vigorously. NOTE: Make sure stones are completely coated.

4. Pour contents into wheelbarrow and move wheelbarrow to job site.

5. Pour batch on slab, rake out to approximate thickness and screed to desired thickness. Tamp into place with heavy magnesium alloy trowel and trowel to a tight, close



CAUTION

1. Do not use mixer with rubber blades or any rubber grommets, shims, etc.
2. Leave edge of each trowelled mix ragged so each new mix can be feathered to previous mix.
3. Do not use this product when temperatures are below 55 degrees F.
4. During threatening weather have wide roll of Visqueen available in event of rain.
5. If the job is not completed in one day it is desirable to strip job with metal, plastic, or wood strips. This would eliminate any unattractive cold joints.
6. Forms should be oiled with any oil or vaseline to give quick release.
7. If conditions warrant, doubling mix to 300 pounds of aggregate to 2 Portion Packs is feasible.
8. If there is a delay in continuity of use of mixer, clean out residue with soap,

finish with a rounded
corner or swimming pool
steel trowel.

water and a small amount of aggregate.
Turn mixer and run until barrel is clean.
Repeat if necessary.

**THE INFORMATION GIVEN HEREIN IS
BASED ON DATA BELIEVED TO BE
RELIABLE. HOWEVER,
SUPERSTONE, INC. MAKES NO
WARRANTIES EXPRESSED OR
IMPLIED AS TO ITS ACCURACY AND
ASSUMES NO LIABILITY ARISING
OUT OF IT'S USE BY OTHERS. THIS
PUBLICATION IS NOT TO BE TAKEN
AS A LICENSE TO OPERATE UNDER,
OR RECOMMENDATION TO
INFRINGE ANY PATENTS.**